


Codice	Ø Int.	Spess. Min.	Spess. Max	Peso	P.E.	P.S.	Depr.	R. Curvatura	Lg. Rotolo	Vol.	
Code	Ø Int.	Min wall th.	Max wall th.	Weight	W.P.	B.P.	Vac.	Bending	Coil lgth.	Vol.	
	mm/inch	mm	mm	g/m	[bar]	[bar]	m H ₂ O	mm	m	m ³	
MT010190000000	19,1*/3/4"	4,0	4,3	390	8,0	24	10	140	50	0,071	
MT010200000000	20*	4,0	4,3	400	8,0	24	10	140	50	0,073	
MT010220000000	22*	4,1	4,4	450	8,0	24	10	160	50	0,079	
MT010250000000	25*	4,3	4,6	530	8,0	24	10	170	50	0,109	
MT010254000000	25,4*/1"	4,3	4,6	540	8,0	24	10	170	50	0,111	
MT010300000000	30*	4,4	4,7	640	8,0	24	10	195	50	0,126	
MT010320000000	31,8*/1.1/4"	4,4	4,7	670	8,0	24	10	205	50	0,132	
MT010350000000	35*	4,4	4,8	730	7,0	21	10	220	50	0,171	
MT010380000000	38,1*/1.1/2"	4,4	4,8	790	7,0	21	10	235	50	0,206	
MT010400000000	40*	4,3	4,8	810	7,0	21	10	250	50	0,214	
MT010450000000	45*	4,4	4,8	910	6,0	18	10	275	50	0,236	
MT010500000000	50*	4,9	5,3	1130	6,0	18	10	300	50	0,436	
MT010520000000	50,8*/2"	4,9	5,3	1150	6,0	18	10	300	50	0,442	
MT010550000000	55*	5,3	5,8	1370	6,0	18	10	330	50	0,384	
MT010600000000	60*	5,4	5,9	1510	6,0	18	10	355	50	0,620	
MT010630000000	63,5*/2.1/2"	5,6	6,0	1640	6,0	18	10	370	50	0,652	
MT010700000000	70*/2.3/4"	5,8	6,3	1850	5,0	15	10	410	50	0,714	
MT010760000000	76,2*/3"	5,8	6,3	2000	5,0	15	10	440	50	0,767	
MT010800000000	80*	5,9	6,6	2130	5,0	15	10	460	30	0,671	
MT010900000000	90*	6,2	6,9	2520	4,0	12	10	530	30	0,747	
MT011000000000	100*	7,1	7,9	3220	4,0	12	9	600	30	0,889	
MT011020000000	102*/4"	7,1	7,9	3280	4,0	12	9	600	30	0,905	
MT011100000000	110*	7,2	8,0	3560	4,0	12	9	690	30	1,290	
MT011270000000	127*/5"	7,3	8,1	4140	4,0	12	9	800	30	1,466	
MT011500000000	151,5*	9,0	10,0	6200	3,0	9	8,5	1300	20	1,372	
MT011520000000	152,4*/6"	9,0	10,0	6230	3,0	9	8,5	1300	20	1,379	
MT012030000000	203,2*/8"	10,7	12,5	10030	2,0	6	7	1200	10	1,826	

*Disponibile su richiesta, per quantitativi da concordare con l'ufficio vendite / *Available on request, contact our sales office for more info and quantities

I dati tecnici qui riportati sono stati misurati a 23°C e al 50% di umidità / The technical data here reported were measured at 23°C with 50% humidity