

FICHA TÉCNICA · TECHNICAL DATA




en stock
available on stock




CLAMP BS 4825 p.123

ARTÍCULOS DE LA MISMA SERIE ITEMS IN THE SAME SERIES



PLUTONE A (cód. PY 01) p.96



PLUTONE BIO (cód. B2) p.100

CÓDIGO	Ø INT.	Ø EST.	PESO	P.T.	P.R.	VACIO	R. CURVATURA	L.G. ROLLO	VOLUMEN
CODE	Ø INT.	Ø OUT.	WEIGHT	W.P.	B.P.	VACUUM	BENDING	COIL LGTH.	VOLUME
	mm	mm	g/m	bar	bar	m H ₂ O	mm	m	m ³
PY060060012200	6	12,2	125	4	20	9,5	20	60	0,019
PY060080014200	8	14,2	150	4	20	9,5	30	60	0,024
PY060100016000	10	16	170	4	20	9,5	40	60	0,028
PY060120018000	12	18	195	4	20	9,5	40	60	0,033
PY060130019000*	13	19	210	4	20	9,5	50	60	0,038
PY060140020000	14	20	220	4	20	9,5	50	60	0,039
PY060160022400	16	22,4	265	4	20	9,5	60	60	0,048
PY060180024400	18	24,4	290	4	20	9,5	60	60	0,070
PY060190026000*	19	26	330	4	20	9,5	70	60	0,075
PY060200027000	20	27	345	4	20	9,5	70	60	0,086
PY060220029000	22	29	375	4	20	9,5	80	60	0,093
PY060250033000	25	33	495	3	15	9,5	90	60	0,127
PY060300038000	30	38	580	3	15	8,5	110	60	0,146
PY060320040400	32	40,4	640	3	15	8,5	110	60	0,155
PY060350043400	35	43,4	690	3	15	8,5	120	60	0,167
PY060380047000	38	47	795	3	15	8,5	130	30	0,120
PY060400049000	40	49	835	3	15	8,5	140	30	0,125
PY060420051200*	42	51,2	890	3	15	8,5	150	30	0,131
PY060450054800	45	54,8	1090	3	15	8	160	30	0,175
PY060500060000	50	60	1220	3	15	8	180	30	0,259
PY060508060800*	50,8	60,8	1240	3	15	8	180	30	0,263
PY060600071800	60	71,8	1680	2,5	12	8	210	30	0,310
PY060630074800	63	74,8	1775	2,5	12	8	220	30	0,323
PY060650076800*	65	76,8	1830	2,5	12	7	230	30	0,332
PY060700082000	70	82	1985	2,5	12	7	250	30	0,354
PY060760088200	76	88,2	2175	2,5	12	7	270	30	0,508
PY060800092200	80	92,2	2310	2,5	12	7	280	20	0,398
PY060900103000	90	103	2955	2	10	7	360	20	0,527
PY061020115000	102	115	3325	1,5	8	7	410	20	0,589
PY061050118000*	105	118	3415	1,5	8	7	420	20	0,604
PY061100127400	110	127,4	4725	1	5	9	500	20	0,652
PY061200137400	120	137,4	5120	0,5	3	9	540	20	1,055
PY061270144400	127	144,4	5455	0,5	3	9	570	20	1,109
PY061500168600	151	169,6	6800	0,5	3	9	680	20	1,303

*Disponible bajo pedido, para cantidades a convenir con el departamento de ventas.

*Available on request, contact our sales office for more info and quantities.

Los datos técnicos indicados se midieron a 23°C y 50% de humedad.

The technical data here reported have been measured at 23°C with 50% umidity.